Test Report

Kunshan EMF Industrial Co., Ltd. +86 512 571 131 82 Tel
91 Xinpu Road, Kunshan City +86 512 571 131 83 Fax
P.R.China. 215337 +86 138 626 007 66 Mobile
www.emfcn.com sales@emfcn.com e-Mail

Test Report No.: ETR2023092501HLW
Date: Sep 25, 2023

Sample Name:
NON-Kinking floating line (8-strand rope)

Sample Color:
Orange

Product Specification:
Dia.8mm x 200mtr, 8mm x 50mtr, 8 x 100mtr
Dia. 10mm x 150mtr, 10mm x 50mtr, 10 x 100mtr

Material:
Polypropylene.

Quantity of Sample:
4 pcs of dia. 8mm, Specimen Number 1 to 4)
and
4 pcs of dia. 10mm Specimen Number 5 to 8)

Above samples were randomly taken from the finished goods. EMF Marine testing team assumes these samples represent the average quality of this batch of finished goods.

Date of Sampling: Sep 25, 2023

Testing Start Date: Sep 25, 2023

Testing End Date: Sep 25, 2023

Test result(s): For further details, please refer to the following page(s).
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
Kunshan EMF Industrial Co., Ltd.

Francis Lei
Authorized signatory

emf MARINE®

Test Report No.: ETR2023092501HLW
Date: Sep 25, 2023

Test Item: Tensile Strength

Specimen Number	Breaking Force (kN)	Specimen Number	Breaking Force (kN)
1. (Dia. 8mm)	6.06	5. (Dia. 10mm)	8.38
2. (Dia. 8mm)	6.12	6. (Dia. 10mm)	8.34
3. (Dia. 8mm)	6.06	7. (Dia. 10mm)	8.25
4. (Dia. 8mm)	6.09	8. (Dia. 10mm)	8.33





Sample Photos

********End of the Report********